

# d-AlCoCu phase formation in alternating Al-Co-Al-Cu multilayers due to ion irradiation

Pavol Noga<sup>1</sup>, Ivona Černíčková<sup>2</sup>, Juraj Halanda<sup>1</sup>, Pavol Priputen<sup>2</sup>, Jozef Janovec<sup>3</sup>

<sup>1</sup>*Slovak University of Technology in Bratislava, Faculty of Materials Science and Technology in Trnava, Advanced Technologies Research Institute, Jána Bottu 25, 91724 Trnava*

<sup>2</sup>*Slovak University of Technology in Bratislava, Faculty of Materials Science and Technology in Trnava, Institute of Materials Science, Jána Bottu 25, 91724 Trnava, Slovakia*

<sup>3</sup>*Slovak University of Technology in Bratislava, University Science Park, Vazovova 5, 81243 Bratislava, Slovakia*

[pavol.noga@stuba.sk](mailto:pavol.noga@stuba.sk)

Ion-beam mixing induced quasicrystalline phases were studied predominantly in binary systems, such as Al-Mn [1, 2], Co-Cu [3], Fe-Cu [4] and Al-Fe [5], in multilayer structures composed of alternating layers of the constituting elements. In this work we focus on the formation and evolution of the d-AlCoCu quasicrystalline phase [6] in a ternary multilayer structure subjected to MeV heavy ion-beam irradiation at different temperatures. The samples were prepared using magnetron sputtering deposition of 26 alternating layers of Al, Co and Cu, with the overall chemical composition  $\text{Al}_{64}\text{Co}_{16}\text{Cu}_{20}$ , onto a monocrystalline Si (100) substrate, with Al always being the interlayer between Co and Cu as well as the bottom and the top layer. These were then subjected to 30 MeV  $\text{Cu}^{5+}$  ion irradiation with fluences from  $1 \times 10^{13}$  to  $5 \times 10^{14}$  ions. $\text{cm}^{-2}$  at 300°C, 400°C and 500°C. The samples were analyzed by scanning electron microscopy (SEM), x-ray diffraction (XRD) and energy-dispersive x-ray spectrometry (EDS). Ion irradiation at fluences above  $1 \times 10^{14}$  ions. $\text{cm}^{-1}$  caused mixing of Al with Co and Cu and dissolving the initial multilayer structure at 300°C. At 400°C and 500°C, however, an interface sharpening at the Co layers was observed, whereby this effect is more pronounced at higher temperature. The Al and Cu layers mixed well in any case. A possible explanation for this behavior is the evolution of the  $\text{Al}_2\text{Cu}$  phase with increasing temperature, which probably slows down Co diffusion into adjacent layers. Presence of the d-AlCoCu phase was confirmed by XRD in all samples irradiated with  $5 \times 10^{14}$  ions. $\text{cm}^{-2}$  fluence. XRD peak heights and number of crystallographic orientations is increasing with temperature, which might indicate that increasing irradiation fluence and temperature could lead to a quasicrystalline film.

1. D. A. Lilienfeld, M. Nastasi, H. H. Johnson, D. G. Ast, J. W. Mayer, *Phys. Rev. Lett.*, **55**, (1985), 1587.
2. J. A. Knapp, D. M. Follstaedt, *Nucl. Instrum. Meth. Phys. Res. B*, **19/20**, (1987), 611.
3. Z. F. Li, B. X. Liu, *Nucl. Instrum. Meth. Phys. Res. B*, **178**, (2001), 224.
4. G. W. Yang, W. S. Lai, C. Lin, B. X. Liu, *Appl. Phys. Lett.*, **74**, (1999), 3305.
5. A. Traverse, E. Belin-Ferré, Z. Dankázi, L. Mendoza-Zélis, O. Laborde, R. Portier, *J. Phys. Condens. Matter*, **8**, (1996), 3843.
6. P. Priputen, T.Y. Liu, I. Černíčková, D. Janičkovič, V. Kolesár, J. Janovec, *J. Phase Equilib. Diff.*, **34**, (2013), 1547.

*This work was supported by the European Regional Development Fund, Research and Development Operational Programme under contracts ITMS:26220120048 and ITMS:2622022079, the Slovak Research and Development Agency under contract No. APVV-15-0049, the Grant Agency VEGA under contracts No. 1/0018/15, 1/0219/16 and 1/0330/18.*